B41

PCT

(51) International Patent Classification ^{7} : G01B 11/06, B24B 37/00, H01L 21/304	A1	(11) International Publication Number: WO 00/26613
		(43) International Publication Date: 11 May 2000 (11.05.00)

(72) Inventors: WISWESSER, Andreas, Norbert; Kurt–Handwerk–Strasse 39, D–09599 Freiberg (DE). PAN, Judon, Tony; 20279 Carol Lane, Saratoga, CA 95070 (US). SWEDEK, Boguslaw; 1649 Willow Lake Lane, San Jose, CA 95131 (US). BIRANG, Manoocher; 18836 Favre Ridge Road, Los Gatos, CA 95030 (US).

(54) Title: OPTICAL MONITORING OF RADIAL RANGES IN CHEMICAL MECHANICAL POLISHING A METAL LAYER ON A SUBSTRATE

(57) Abstract

A surface of a substrate (10) is brought into contact with a polishing pad (34) that has a window (36), causes relative motion between the substrate (10) and the polishing pad (34), and directs a light beam through the window so that the motion of the polishing pad relative to the substrate causes the light beam (42) to move in a path across the substrate (10). Light beam reflections (56) from the substrate (10) or from comparing two substrates (10) are detected (46), and used to determine polishing parameters, detect process repeatability, and qualify processes. The reflection data are be divided into a plurality of radial ranges when identifying an endpoint in polishing a metal layer on substrate (10).

OPTICAL MONITORING OF RADIAL RANGES IN CHEMICAL MECHANICAL POLISHING A METAL LAYER ON A SUBSTRATE

BACKGROUND

5   The present invention relates generally to chemical mechanical polishing of substrates, and more particularly to methods and apparatus for detecting an end-point of a metal layer during a chemical mechanical polishing operation.

An integrated circuit is typically formed on a
10   substrate by the sequential deposition of conductive, semiconductive or insulative layers on a silicon wafer. After each layer is deposited, the layer is etched to create circuitry features. As a series of layers are sequentially deposited and etched, the outer or uppermost surface of the
15   substrate, i.e., the exposed surface of the substrate, becomes increasingly non-planar. This non-planar surface presents problems in the photolithographic steps of the integrated circuit fabrication process. Therefore, there is a need to periodically planarize the substrate surface.

20   Chemical mechanical polishing (CMP) is one accepted method of planarization. This planarization method typically requires that the substrate be mounted on a carrier or polishing head. The exposed surface of the substrate is placed against a rotating polishing pad. The
25   polishing pad may be either a "standard" pad or a fixed-abrasive pad. A standard pad has a durable roughened surface, whereas a fixed-abrasive pad has abrasive particles held in a containment media. The carrier head provides a controllable load, i.e., pressure, on the substrate to push
30   it against the polishing pad. A polishing slurry, including at least one chemically-reactive agent, and abrasive particles if a standard pad is used, is supplied to the surface of the polishing pad.

One problem in CMP is determining whether the
35   polishing process is complete, i.e., whether a substrate layer has been planarized to a desired flatness or

thickness. Variations in the initial thickness of the
substrate layer, the slurry composition, the polishing pad
condition, the relative speed between the polishing pad and
the substrate, and the load on the substrate can cause

5   variations in the material removal rate. These variations
cause variations in the time needed to reach the polishing
endpoint. Therefore, the polishing endpoint cannot be
determined merely as a function of polishing time.

         One way to determine the polishing endpoint is to

10   remove the substrate from the polishing surface and examine
it. For example, the substrate may be transferred to a
metrology station where the thickness of a substrate layer
is measured, e.g., with a profilometer or a resistivity
measurement. If the desired specifications are not met, the

15   substrate is reloaded into the CMP apparatus for further
processing. This is a time consuming procedure that reduces
the throughput of the CMP apparatus. Alternatively, the
examination might reveal that an excessive amount of
material has been removed, rendering the substrate unusable.

20   Several methods have been developed for in-situ
polishing endpoint detection. Most of these methods involve
monitoring a parameter associated with the substrate
surface, and indicating an endpoint when the parameter
abruptly changes. For example, where an insulative or

25   dielectric layer is being polished to expose an underlying
metal layer, the coefficient of friction and the
reflectivity of the substrate will change abruptly when the
metal layer is exposed.

         Where the monitored parameter changes abruptly at

30   the polishing endpoint, such endpoint detection methods are
acceptable. However, as the substrate is being polished,
the polishing pad condition and the slurry composition at
the pad-substrate interface may change. Such changes may
mask the exposure of an underlying layer, or they may

35   imitate an endpoint condition. Additionally, such endpoint
detection methods will not work if only planarization is

being performed, if the underlying layer is to be over-
polished, or if the underlying layer and the overlying layer
have similar physical properties.

5   SUMMARY
          A method is disclosed for determining an endpoint
associated with chemical mechanical polishing a metal layer
on a substrate, the endpoint having a predetermined pattern
reflected of reflected high intensity. In one aspect, the
10   method includes bringing a surface of the substrate into
contact with a polishing pad that has a window; causing
relative motion between the substrate and the polishing pad;
directing a light beam through the window, the motion of the
polishing pad relative to the substrate causing the light
15   beam to move in a path across the substrate; detecting light
beam reflections from the metal layer; generating reflection
data associated with the light beam reflections; dividing
the reflection data into a plurality of radial ranges; and
identifying the predetermined pattern from the reflection
20   data in the plurality of radial ranges to establish the
endpoint.
          Implementations of the invention includes one or
more of the following. The chemical mechanical polishing
operation is stopped when the endpoint is identified. The
25   reflection data may be stored on a media for subsequent
analysis. Processing of the reflection data may be done in
real-time or off-line. The identifying step may include
comparing the reflection data to a predetermined threshold.
The identifying step may include determining whether the
30   reflection data is in a downward trend, an upward trend, or
a flat trend. The detecting step measures reflections
corresponding to a sampling zone in the path across the
substrate and may include determining a radial position for
each sampling zone; determining a position of the carrier
35   head from a carrier head sweep profile; and dividing the
reflection measurements into a plurality of radial ranges

4

according to the radial position.

In another aspect, a method determines an endpoint associated with chemical mechanical polishing a metal layer, the endpoint having a predetermined pattern of reflected

5   light intensity. The method includes directing a light beam through a window of a polishing pad and moving the polishing pad relative to the substrate to cause the light beam to move in a path across the substrate; detecting light beam reflections from the metal layer; generating reflection data

10   associated with the light beam reflections; dividing the reflection data into a plurality of radial ranges; and identifying the predetermined pattern from the reflection data in the plurality of radial ranges to establish the endpoint.

15   Implementations of the invention include one or more of the following. The chemical mechanical polishing may be stopped when the endpoint is identified. The reflection data may be stored on a media for subsequent analysis. The identifying step includes comparing the reflection data to a

20   predetermined threshold. The identifying step may also include determining whether the reflection data has a downward trend, an upward trend or a flat trend.

In another aspect, an apparatus for polishing a metal layer of a substrate includes a carrier head to hold

25   the substrate; a polishing pad adapted to contact a surface of the substrate, the polishing pad having a window therethrough; a motor coupled to the polishing pad for causing relative motion between the substrate and the polishing pad; a light source to direct a light beam through

30   the window, the motion of the polishing pad relative to the substrate causing the light beam to move in a path across the substrate; a sensor optically coupled to the light source for detecting light beam reflections from the substrate, the sensor generating reflection data associated

35   with the light beam reflections; an electronic bin coupled to the sensor for separating the reflection data into a

plurality of radial ranges; and a pattern recognizer coupled to the sensor and to the bin for identifying the endpoint by comparing the predetermined pattern to the reflection data.

5   Implementations of the invention include one or more of the following. A polishing controller may be connected to the pattern recognizer, the polishing controller stopping chemical mechanical polishing when the endpoint is identified. The reflection data may be stored on a media for subsequent analysis. The pattern recognizer compares the

10   reflection data to a predetermined threshold. The pattern recognizer may determine whether the reflection data has a downward trend, an upward trend or a flat trend.

In another aspect, the invention is directed to a method of determining polishing parameters. In the method,

15   a surface of a substrate is brought into contact with a polishing pad that has a window, relative motion is created between the substrate and the polishing pad, and a light beam is directed through the window. The motion of the polishing pad relative to the substrate causes the light

20   beam to move in a path across the substrate. Light beam reflections from a layer in the substrate are detected, reflection data associated with the light beam reflections is generated, and the reflection data from a scan of the light beam across the substrate is displayed. Polishing

25   parameters are selected to provide uniform polishing of the substrate based on the displayed reflection data.

In another aspect, the invention relates to a method of determining process uniformity. In the method, light beam reflections are detected during polishing of a layer in

30   first and second substrates. Reflection data associated with the light beam reflections is generated, and the reflection data is displayed from a first scan of the light beam across the first substrate and from a second scan of the light beam across the second substrate. The reflection

35   data from the first scan is compared to the reflection data from the second scan to determine process uniformity. A

6

polishing consumable may be changed between the polishing of the first and second substrates.

Advantages of the invention include one or more of the following. The reflection data from a wafer is captured
5 using a high resolution data acquisition system at a relatively fine time scale, on the order of milliseconds. Further, reflection intensity changes during polishing are captured for different radial positions on the substrate. The high resolution data acquisition system provides precise
10 time control of each process step in a multi-step operation. Detailed data is available on the progress of the metal polishing operation at different locations of the wafer. Additionally, parameters such as uniformity of the entire wafer and removal rate for different radial portions of the
15 wafer are determined. The acquired high resolution data can be processed on-line or off-line to adjust various variables and parameters to minimize erosion and dishing of the surface layer. If the data is processed in real-time, the feedback data may be used for endpoint detection or for
20 closed-loop control of process parameters. For instance, the polishing pressure, polishing speed, chemistry, and slurry composition may be altered in response to the feedback data to optimize the overall polishing performance and/or polishing quality. The reflection data is available
25 for experimentation to improve the deposition process.

Other features and advantages of the invention will become apparent from the following description, including the drawings and claims.

30   BRIEF DESCRIPTION OF THE DRAWINGS
FIG. 1 is an exploded perspective view of a chemical mechanical polishing apparatus.
FIG. 2 is a side view of a chemical mechanical polishing apparatus including an optical reflectometer.
35   FIG. 3 is a simplified cross-sectional view of a substrate being processed, schematically showing a laser

beam impinging on and reflecting from the substrate.

     FIG. 4 is a graph showing a measured reflectance
trace in arbitrary intensity units (a.u.).

     FIGS. 5A-5E are simplified plan views illustrating
the position of a window in a polishing pad as a platen
rotates.

     FIG. 6 is a flow chart of a method of determining
the end-point of the polishing of a metal layer during CMP.

     FIG. 7A is a schematic view illustrating the path of
a laser beneath the carrier head.

     FIG. 7B is a graph showing a hypothetical portion of
a reflectance trace generated by a single sweep of the
window beneath the carrier head.

     FIG. 8 is a schematic view illustrating the radial
positions of sampling zones from the path of the laser.

     FIG. 9A is a flow chart of a method of determining
the radial position of a sampling zone.

     FIG. 9B is a graph showing the time at which the
laser beam passes beneath the leading and trailing edges of
the substrate as a function of the number of rotations of
the platen.

     FIG. 10 is a schematic view illustrating the
calculation of the radial position of the sampling zones.

     FIG. 11 is a schematic diagram of a data structure
to store intensity measurements.

     FIG. 12 is a graph illustrating an overlay of
several reflectance traces taken at different times.

     FIGS. 13A-13H are graphs showing the reflected
intensity of the metal layer as a function of distance from
the center of the substrate over a polishing period.

DETAILED DESCRIPTION

     Referring to FIGS. 1 and 2, one or more substrates
10 may be polished by a CMP apparatus 20. A description of
a similar polishing apparatus 20 may be found in U.S. Patent
No. 5,738,574, the entire disclosure of which is

incorporated herein by reference. Polishing apparatus 20
includes a series of polishing stations 22 and a transfer
station 23. Transfer station 23 serves multiple functions,
including receiving individual substrates 10 from a loading
5   apparatus (not shown), washing the substrates, loading the
substrates into carrier heads, receiving the substrates from
the carrier heads, washing the substrates again, and
finally, transferring the substrates back to the loading
apparatus.

10   Each polishing station includes a rotatable platen
24 on which is placed a polishing pad 30. The first and
second stations may include a two-layer polishing pad with a
hard durable outer surface, whereas the final polishing
station may include a relatively soft pad. If substrate 10
15   is an "eight-inch" (200 millimeter) or "twelve-inch" (300
millimeter) diameter disk, then the platens and polishing
pads will be about twenty inches or thirty inches in
diameter, respectively. Each platen 24 may be connected to
a platen drive motor (not shown). For most polishing
20   processes, the platen drive motor rotates platen 24 at about
thirty to two hundred revolutions per minute, although lower
or higher rotational speeds may be used. Each polishing
station may also include a pad conditioner apparatus 28 to
maintain the condition of the polishing pad so that it will
25   effectively polish substrates.

Polishing pad 30 typically has a backing layer 32
which abuts the surface of platen 24 and a covering layer 34
which is used to polish substrate 10. Covering layer 34 is
typically harder than backing layer 32. However, some pads
30   have only a covering layer and no backing layer. Covering
layer 34 may be composed of an open cell foamed polyurethane
or a sheet of polyurethane with a grooved surface. Backing
layer 32 may be composed of compressed felt fibers leached
with urethane. A two-layer polishing pad, with the covering
35   layer composed of IC-1000 and the backing layer composed of
SUBA-4, is available from Rodel, Inc., of Newark, Delaware

(IC-1000 and SUBA-4 are product names of Rodel, Inc.).

A rotatable multi-head carousel 60 is supported by a center post 62 and is rotated thereon about a carousel axis 64 by a carousel motor assembly (not shown). Center post 62
5   supports a carousel support plate 66 and a cover 68. Carousel 60 includes four carrier head systems 70. Center post 62 allows the carousel motor to rotate carousel support plate 66 and to orbit the carrier head systems and the substrates attached thereto about carousel axis 64. Three
10 of the carrier head systems receive and hold substrates, and polish them by pressing them against the polishing pads. Meanwhile, one of the carrier head systems receives a substrate from and delivers a substrate to transfer station 23.

15 Each carrier head system includes a carrier or carrier head 80. A carrier drive shaft 74 connects a carrier head rotation motor 76 (shown by the removal of one quarter of cover 68) to each carrier head 80 so that each carrier head can independently rotate about it own axis.
20 There is one carrier drive shaft and motor for each head. In addition, each carrier head 80 independently laterally oscillates in a radial slot 72 formed in carousel support plate 66. A slider (not shown) supports each drive shaft in its associated radial slot. A radial drive motor (not
25 shown) may move the slider to laterally oscillate the carrier head.

The carrier head 80 performs several mechanical functions. Generally, the carrier head holds the substrate against the polishing pad, evenly distributes a downward
30 pressure across the back surface of the substrate, transfers torque from the drive shaft to the substrate, and ensures that the substrate does not slip out from beneath the carrier head during polishing operations.

Carrier head 80 may include a flexible membrane 82
35 that provides a mounting surface for substrate 10, and a retaining ring 84 to retain the substrate beneath the

10

mounting surface. Pressurization of a chamber 86 defined by
flexible membrane 82 forces the substrate against the
polishing pad. Retaining ring 84 may be formed of a highly
reflective material, or it may be coated with a reflective
5   layer to provide it with a reflective lower surface 88. A
description of a similar carrier head 80 may be found in
U.S. Patent Application Serial No. 08/745,679, entitled a
CARRIER HEAD WITH a FLEXIBLE MEMBRANE FOR a CHEMICAL
MECHANICAL POLISHING SYSTEM, filed November 8, 1996, by
10   Steven M. Zuniga et al., assigned to the assignee of the
present invention, the entire disclosure of which is
incorporated herein by reference.

         A slurry 38 containing a reactive agent (e.g.,
deionized water for oxide polishing) and a chemically-
15   reactive catalyzer (e.g., potassium hydroxide for oxide
polishing) may be supplied to the surface of polishing pad
30 by a slurry supply port or combined slurry/rinse arm 39.
If polishing pad 30 is a standard pad, slurry 38 may also
include abrasive particles (e.g., silicon dioxide for oxide
20   polishing).

         In operation, the platen is rotated about its
central axis 25, and the carrier head is rotated about its
central axis 81 and translated laterally across the surface
of the polishing pad.
25   A hole 26 is formed in platen 24 and a transparent
window 36 is formed in a portion of polishing pad 30
overlying the hole. Transparent window 36 may be
constructed as described in U.S. Patent Application Serial
No. 08/689,930, entitled METHOD OF FORMING A TRANSPARENT
30   WINDOW IN A POLISHING PAD FOR A CHEMICAL MECHANICAL
POLISHING APPARATUS by Manoocher Birang, et al., filed
August 26, 1996, and assigned to the assignee of the present
invention, the entire disclosure of which is incorporated
herein by reference. Hole 26 and transparent window 36 are
35   positioned such that they have a view of substrate 10 during
a portion of the platen's rotation, regardless of the

11

translational position of the carrier head.

A reflectometer 40 is secured to platen 24 generally
beneath hole 26 and rotates with the platen. The
reflectometer includes a light source 44 and a detector 46.
5   The light source generates a light beam 42 which propagates
through transparent window 36 and slurry 38 (see FIG. 3) to
impinge upon the exposed surface of substrate 10. For
example, the light source 44 may be laser and the light beam
42 may be a collimated laser beam. The light laser beam 42
10 is projected from laser 44 at an angle α from an axis normal
to the surface of substrate 10, i.e., at an angle α from
axes 25 and 81. In addition, if the hole 26 and window 36
are elongated, a beam expander (not illustrated) may be
positioned in the path of the light beam to expand the light
15 beam along the elongated axis of the window. Laser 44 may
operate continuously. Alternatively, the laser may be
activated to generate laser beam 42 during a time when hole
26 is generally adjacent substrate 10.

Referring to FIGS. 2 and 5A-5E, CMP apparatus 20 may
20 include a position sensor 160, such as an optical
interrupter, to sense when window 36 is near the substrate.
For example, the optical interrupter could be mounted at a
fixed point opposite carrier head 80. A flag 162 is
attached to the periphery of the platen. The point of
25 attachment and length of flag 162 is selected so that it
interrupts the optical signal of sensor 160 from a time
shortly before window 36 sweeps beneath carrier head 80 to a
time shortly thereafter. The output signal from detector 46
may be measured and stored while the optical signal of
30 sensor 160 is interrupted.

In operation, CMP apparatus 20 uses reflectometer 40
to determine the amount of material removed from the surface
of the substrate, or to determine when the surface has
become planarized. A general purpose programmable digital
35 computer 48 may be connected to laser 44, detector 46 and
sensor 160. Computer 48 may be programmed to activate the

12

laser when the substrate generally overlies the window, to
store intensity measurements from the detector, to display
the intensity measurements on an output device 49, to store
the intensity measurement, to sort the intensity
5   measurements into radial ranges, and to detect the polishing
endpoint.

Referring to FIG. 3, a substrate 10 includes a
silicon wafer 12 and an overlying metal layer 16 disposed
over an oxide or nitride layer 14. The metal may be copper,
10   tungsten, aluminum, among others. As different portions of
the substrate with different reflectivities are polished,
the signal output from the detector 46 varies with time.
Particularly, when the metal layer 16 has been polished away
to expose the oxide or nitride layer 14, the reflectivity of
15   the substrate drops. The time varying output of detector 46
may be referred to as an in-situ reflectance measurement
trace (or more simply, a reflectance trace). As discussed
below, this reflectance trace may be used to determine the
end-point of the metal layer polishing operation.

20   Referring to FIGS. 4 and 5A-5E, a measured
reflectance trace with a transient intensity waveform 90
generated by polishing a metal-coated wafer is shown. The
intensity waveform 90 is generated over a relatively long
time scale (measured in seconds). Characteristic features
25   of the waveform include top level plateau 97, each of which
is surrounded by left and right intermediate plateau 98.
One cycle of the waveform 90 includes left and right
intermediate level plateau 98, one of the top level plateau
97, and a background level 94.

30   The intermediate plateau 98 represent reflections
from the retaining ring 84, while the top level plateau 97
represent reflections from the substrate 10. The background
level represents scattered reflections from the window and
slurry. The reflection from retaining ring 84 is higher
35   than background level. As the substrate 10 is polished and
the metal layer 16 is removed to expose the underlying layer

14, the end-point waveform 90 drops toward or below the level of the intermediate plateau 98.

Referring to FIGS. 4 and 5A-5E, the large scale structure of reflectance trace 90 can be explained by
5   reference to the angular position of platen 24. Initially, window 36 does not have view of the substrate (see FIG. 5A). Consequently, laser beam 42 is not reflected and the intensity measured by detector 46 is a result of background intensity, including reflection from slurry 38 and
10 transparent window 36. This low intensity corresponds to the background level 94. As platen 24 rotates, window 36 first sweeps underneath retaining ring 84 of carrier head 80 (see FIG. 5B). The lower surface 88 of retaining ring 84 reflects a portion of laser beam 42 into detector 46,
15 creating an intermediate intensity measurement that corresponds to intermediate plateau 98. As window 36 sweeps beneath substrate 10 (see FIG. 5C) a portion of laser beam 42 is reflected by the substrate. In general, the metal layer of substrate 10 will have a high reflectivity,
20 resulting in top level plateau 97 on reflectance trace 90. As the platen continues to rotate, window 36 passes again beneath retaining ring 84 (see FIG. 5D). Finally, window 36 sweeps out from beneath carrier head 80 (see FIG. 5E), and the detector measures a low intensity that corresponds to
25 the background 94.

Computer 48 of CMP apparatus 20 may use the reflectance trace generated by reflectometer 40 to determine the end-point of the metal layer polishing operation. Each measurement may be performed at a plurality of radial
30 positions. In addition, computer 48 may use the intensity measurements to determine the flatness of the substrate and the polishing uniformity for CMP tool and process qualification as explained below.

Referring now to Fig. 6, an end-point determining
35 process is shown. First, several polishing parameters that will be used during the end-point determination are stored

14

in the memory of computer 48 (step 101). The polishing
parameters of interest include the platen rotation rate and
the carrier head sweep profile.

A metal layer on a surface of the substrate 12 is
5   polished (step 102) by bringing the surface of the substrate
into contact with the polishing pad 30 (Fig. 2). The
polishing pad 30 is rotated, causing relative motion between
the substrate and the polishing pad.

Transient intensity data is monitored and collected
10 for a plurality of sampling zones (step 104). This is done
by directing a light beam generated by the reflectometer 40
through the window. The motion of the polishing pad 30
relative to the substrate 12 causes the light beam to move
in a path across the substrate surface. Light beam
15 reflections from the substrate 10 and the retaining ring 84
are detected by a sensor, which generates reflection data
associated with the light beam reflections.

The transient intensity data is displayed on a
monitor (step 106) for an operator to monitor the progress
20 of the polishing operation. A pattern recognizer is applied
to the transient intensity data to detect signal changes
(step 108). The pattern recognizer may simply be a
threshold detector which checks whether the intensity data
has fallen below a predetermined threshold. Alternatively,
25 in another embodiment, a window logic can be applied to the
data to detect a sequence of signal changes. Three types of
window logic are used to detect local maxima and minima: a
window logic with a downwardly cusp to detect a downward
trend in the reflection data; a window logic with an
30 upwardly cusp to detect an upward trend in the reflection
data; and a window logic with a substantially flat line to
detect that the reflection data is relatively static. The
signal changes may be averaged. More discussion of pattern
recognition algorithms for endpoint detection may be found
35 in above mentioned U.S. Patent Application Serial No.
08/689,930.

The output of the pattern recognizer is a stop signal which, along with additional feedback data, is provided to a polisher controller (step 110). The polisher controller uses the feedback data to adjust various

5   variables and parameters to minimize erosion and dishing of the surface layer. For instance, the polishing pressure, polishing speed, chemistry, and slurry composition may be deployed to optimize the overall polishing performance and/or polishing quality. The stop signal causes the

10 polisher controller to stop the current metal layer polishing operation (step 112).

Concurrent with steps 106-112, the process of Fig. 6 stores the transient intensity data onto a data storage device, e.g., a computer disk (step 114) for subsequent

15 processing. In brief, the intensity for each sampling zone is determined (step 116), the radial position of each sampling zone is calculated (step 118), and the intensity measurements are sorted into radial ranges (step 150). The sorted intensity measurements are used to measure the

20 polishing uniformity and removal rates at different radial ranges of the substrate (step 152). Each of these steps will be discussed in greater detail below.

Generally, the reflected intensity changes during polishing for different radial positions on the substrate.

25 The metal layer may be removed at different rates for different portions of the substrate. For instance, the metal layer near the center of the substrate may be removed last, while the metal layer near the perimeter or edge of the substrate may be removed first, or vice versa. The

30 reflection data from the entire wafer is captured at a relatively fine time scale in the order of milliseconds and is available for experimentation to improve the deposition process. By analyzing the recorded data, the process can be changed to make it faster, shorter or smoother. As can be

35 appreciated, the stored data is useful for process research and development to optimize the process performance.

16

Referring to FIGS. 7A and 7B, the combined rotation
of the platen and the linear sweep of the carrier head
causes window 36 (and thus laser beam 42) to sweep across
the bottom surface of carrier head 80 and substrate 10 in a
5   sweep path 120. As the laser beam sweeps across the
substrate, reflectometer 40 integrates the measured
intensity over a sampling period, T_{sample}, to generate a
series of individual intensity measurements I_a, I_b, ... I_j.
The sample rate F (the rate at which intensity measurements
10   are generated) of reflectometer 40 is given by $F=1/T_{sample}$.
Reflectometer 40 may have a sample rate between about 10 and
400 Hertz (Hz), corresponding to a sampling period between
about 2.5 and 100 milliseconds. Specifically, reflectometer
40 may have a sampling rate of about 40 Hz and a sampling
15   period of about 25 milliseconds.

Thus, each time that laser 44 is activated,
reflectometer 40 measures the intensity from a plurality of
sampling zones 122a-122j. Each sampling zone corresponds to
the area of the substrate over which the laser beam sweeps
20   during a corresponding sampling period. In summary, in step
106, reflectometer 40 generates a series of intensity
measurements I_a, I_b, ... I_j corresponding to sampling zones
122a, 122b, ..., 122j.

Although FIG. 7A illustrates ten sampling zones, there
25   could be more or fewer zones, depending on the platen
rotation rate and the sampling rate. Specifically, a lower
sampling rate will result in fewer, wider sampling zones,
whereas a higher sampling rate will result in a greater
number of narrower sampling zones. Similarly, a lower
30   rotation rate will result in a larger number of narrower
sampling zones, whereas a higher rotation rate will result
in a lower number of wider sampling zones. In addition,
multiple detectors could be used to provide more sampling
zones.

35   As shown in FIG. 7B, the intensity measurements I_a
and I_j for sampling zones 122a and 122j, respectively, are

17

low because window 36 does not have a view of the carrier
head, and consequently laser beam 42 is not reflected.
Sampling zones 122b and 122i are located beneath retaining
ring 84, and therefore intensity measurements I_b and I_i will
5   be of intermediate intensity. Sampling zones 122c, 122d,
... 122h are located beneath the substrate, and consequently
generate relatively large intensity measurements I_c, I_d, ...
I_h at a variety of different radial positions across the
substrate.

10   Fig. 12 is an overlay of several transient signal
graphs 300-320. Each of the transient signal graphs 300-320
represents intensity data over an interval associated with a
sweep of the window beneath the carrier head. For instance,
the graph 300 shows the end-point data between about 1.7
15   seconds to about 2.7 seconds, and the graph 320 shows the
end-point data between about 350.8 seconds and about 351.8
seconds. Of course, the transient signal graphs can be
stored in computer 48 for later reference.

          Fig. 12 shows how the endpoint reflected intensity
20   signal changes during the polishing operation. Initially,
in period 300, the metal layer on the surface of the
substrate 10 is jagged. The metal layer 16 has some initial
topography because of the topology of the underlying
patterned layer 14. Due to this topography, the light beam
25   scatters when it impinges the metal layer. As the polishing
operation progresses, the metal layer becomes more planar
and the reflectivity of the polished metal layer increases
during periods 302-308. As such, the signal strength
steadily increases to a stable level. From period 310-320,
30   as the metal layer 16 is increasingly cleared to expose the
oxide layer 14, the overall signal strength declines until
the polishing operation is completed. Thus, in period 320,
only a small trace of metal remains in the center of the
substrate 10.

35   When entire surface of the substrate is covered with
a metal layer, such as copper, the reflection from the

18

substrate 10 has a square profile. As the metal layer is
removed from the edge of the substrate 10, the profile of
the reflection from the substrate takes on a trapezoidal
shape. Eventually, when the metal layer is nearly removed
5   by the polishing operation, the profile of the reflection
from the substrate 10 takes on a triangular shape.

The transient signal graphs 300-320 can be viewed by
the operator on the display 49 either during or after the
polishing operation. The operator can use the displayed
10 transient signal graphs for a variety of diagnostic and
process control decisions (which may be applicable to both
reflectivity measurements in metal polishing and
interference measurements in oxide polishing). The
transient signal graphs can be used to select process
15 parameters in order to optimize polishing uniformity. For
example, a test wafer can be polished when initially
selecting process parameters, such as the plate rotation
rate, carrier head pressure, carrier head rotation rate,
carrier head sweep profile, and slurry composition. High
20 reflectivity areas represent regions where metal remains on
the substrate, and low reflectivity area represent regions
where metal has been removed from the substate. A noisy
transient signal graph indicates that the metal has not been
evenly removed from the substrate, whereas a relatively flat
25 transient signal graph indicates uniform polishing.
Consequently, the operator can draw immediate conclusions,
without resorting to measuring the substrate layer thickness
with a metrology tool, regarding the effectiveness of the
selected process parameters. The operator can then adjust
30 the polishing parameters, polish another test wafer, and
determine whether the new polishing parameters have improved
the polishing uniformity.

An operator may also examine the transient signal
graphs to determine whether the substrate has been polished
35 to planarity, and whether polishing should be halted.
Furthermore, if an operator notes during polishing of an

19

actual device wafer that a portion of the substrate is being
polished too slowly or too quickly, the process parameters
can be changed while polishing is in progress to adjust the
polishing rate profile.

5   The transient signal graphs can also be used as a
measure of process repeatability. For example, if the
transient signal graphs depart significantly from their
expected shapes, this indicates that there is some problem
in the polishing machine or process.

10   In addition, the transient signal graphs can be
used to "qualify" a process. Specifically, when the
polishing machine receives a new set of consumables, e.g.,
if the polishing pad or slurry is replaced, the operator may
wish to verify that the polishing uniformity has not been

15   affected. An operator can compare the transient signal
graphs for the substrates polished before and after the
change in consumables to determine whether the polishing
uniformity has been affected.

          Turning now to FIG. 8, in step 108 the radial

20   positions R_a, R_b, ... R_j of the corresponding sampling zones
122a, 122b, ... 122j are determined. One way to determine
the radial position of a sampling zone is to calculate the
position of the laser beneath the substrate based on the
measurement time $T_{measure}$ and the platen rotation rate and

25   carrier head sweep profile. Unfortunately, the actual
platen rotation rate and carrier head sweep profile may not
precisely match the polishing parameters. Therefore, a
preferred method 130 of determining the radial positions of
the sampling zones is shown in FIG. 9A. First, the time T_{sym}

30   at which laser beam 42 passes beneath a mid-line 124 (see
FIG. 5C) of the substrate is determined (step 132). Then
the radial positions of the sampling zones are determined
from the time difference between the measurement time $T_{measure}$
and the symmetric time T_{sym} (step 134).

35   One method of determining the symmetry time T_{sym} is to
average the times of the first and last large intensity

20

measurements from each sweep, as these intensity
measurements should correspond to the substrate edge.
However, this results in some uncertainty in T_{sym} because the
position of the sampling zones beneath the substrate are not
5   known.

Referring to FIG. 9B, in order to compute the
symmetric time T_{sym} in step 132, computer 48 determines the
first and last large intensity measurements from sweep path
120, i.e., intensity measurements I_c and I_h, and stores the
10   corresponding measurement times T_{lead} and T_{trail}. These lead
and trail times T_{lead} and T_{trail} are accumulated on each sweep
to generate a series of lead times T_{lead1}, T_{lead2}, ... T_{leadN} and
trail times T_{trail1}, T_{trail2}, ... T_{trailN}. Computer 48 stores lead
times T_{lead1}, T_{lead2}, ... T_{leadN} and the associate number of
15   platen rotations 1, 2, ... N for each leading spike 96.
Similarly, computer 48 stores the trail times T_{trail1}, T_{trail2},
... T_{trailN} and the associated number of rotations 1, 2, ... N
of each trailing spike 98. Assuming that platen 24 rotates
at a substantially constant rate, the times $T_{lead\,1}$, $T_{lead\,2}$,
20   ... T_{leadN} form a substantially linear increasing function
(shown by line 136). Similarly, the times T_{trail1}, T_{trail2}, ...
T_{trailN} also form a substantially linear increasing function
(shown by line 137). Computer 48 performs two least square
fits to generate two linear functions $T_{lead}(n)$ and $T_{trail}(n)$ as
25   follows:

$$T_{lead}(n) = a_1 + (a_2 * n)$$
$$T_{trail}(n) = a_3 + (a_4 * n)$$

where n is the number of platen rotations and a_1, a_2, a_3 and
a_4 are fitting coefficients calculated during the least
30   square fit. Once the fitting coefficients have been
calculated, the symmetry time T_{sym} at which laser beam 42
crosses mid-line 124 (shown by phantom line 138) may be
calculated as follows:

$$T_{sym} = \frac{a_1 + a_3}{2} + \frac{a_2 + a_4}{2} \cdot n$$

By using a least square fit over several platen rotations to

calculate the symmetry time T_{sym}, uncertainty caused by the differences in the relative position of the sampling zone beneath the retaining ring are substantially reduced, thereby significantly reducing uncertainty in the symmetry

5   time T_{sym}.

Once computer 48 has calculated the time T_{sym} at which laser beam 42 crosses midline 124, the radial distance R_a, R_b, ... R_j of each sampling zone 122a, 122b, ... 122j from the center 126 of the substrate are calculated in step

10   132. Referring to FIG. 10, the radial position may be calculated as follows:

$$R = \sqrt{d^2 + L^2 - 2dL\cos\theta}$$

where d is the distance between the center of the polishing pad and the center of window 36, L is the distance from the center of the polishing pad to the center of substrate 10,

15   and θ is the angular position of the window. The angular position θ of the window may be calculated as follows:

$$\theta = f_{platen} \cdot 2\pi (T_{measure} - T_{sym})$$

where f_{platen} is the rotational rate of the platen (in rpm). Assuming that the carrier head moves in a sinusoidal pattern, the linear position L of the carrier head may be

20   calculated as follows:

$$L = L_0 + A \cdot \cos(\omega \cdot T_{measure})$$

where ω is the sweep frequency, A is the amplitude of the sweep, and L_0 is the center position of the carrier sweep.

In another embodiment, position sensor 160 could be used to calculate the time T_{sym} when the window crosses

25   midline 124. Assuming that sensor 160 is positioned opposite carrier head 80, flag 162 would be positioned symmetrically across from transparent window 36. The computer 48 stores both the trigger time T_{start} when the flag interrupts optical beam of the sensor, and the trigger time

30   T_{end} when the flag clears the optical beam. The time T_{sym} may

22

be calculated as the average of T_{start} and T_{end}. In yet
another embodiment, the platen and carrier head positions
could be determined at each sample time T_a, T_b, ... T_h, from
optical encoders connected to the platen drive motor and
5   radial drive motor, respectively.

Once the radial positions R_a, R_b, ... R_m of the
sampling zones have been calculated, some of the intensity
measurement may be disregarded. If the radial position R of
a sampling zone is greater than the radius of the substrate,
10   then the intensity measurement for that sampling zone
includes mostly radiation reflected by the retaining ring or
background reflection from the window or slurry. Therefore,
the intensity measurements for any sampling zone that is
mostly beneath the retaining ring is ignored. This ensures
15   that spurious intensity measurements are not used in the
calculation of the thin film layer reflected intensity.

After several sweeps of laser beam 42 beneath the
substrate, computer 48 accumulates a set of intensity
measurements I_1, I_2, ... I_N, each associated with a
20   measurement time T_1, T_2, ... T_N, and a radial position R_1, R_2,
... R_N.   Referring to FIG. 11, as the intensity, time,
and radial position measurements are accumulated in steps
106 and 108, the time and intensity measurements are sorted
into bins in a data structure 140 in step 110. Each bin is
25   associated with a radial range of sampling zones. For
example, intensity measurements for sampling zones located
up to 20 mm from the center of the substrate may be placed
in a first bin 142 (see FIG. 13A) which is discussed below,
intensity measurements made for sampling zones located
30   between 20 and 30 mm from the center of the substrate may be
placed in a second bin 144 (see FIG. 13B), intensity
measurements made for sampling zones located between 30 and
40 mm from the center of the substrate may be placed in a
third bin 146 (see FIG. 13C), and so on. The exact number
35   of bins and the radial ranges of the bins depend upon the
information that the user desires to extract. In general,

23

the radial range of each bin may be selected so that a
sufficient number of intensity measurements are accumulated
in the bin to provide visually meaningful information.

5   The calculations discussed above are performed for
each bin, thereby providing reflected intensity measurements
at a plurality of radial positions across the surface of the
substrate. Graphs of the initial and final reflected
intensity of the thin film layer as a function of radius are
shown in FIGS. 12 discussed above as well as in FIGS. 13A-
10   13H.

Turning now to Figs. 13A-13H, a number of traces
which display how reflected intensity changes during
polishing for different radial positions on the substrate 10
are shown. The charts of Figs. 13A-13H illustrate that the
15   metal layer is removed at different rates for different
portions of the substrate. Generally, Figs. 13A-13H show
that the metal layer near the center of the substrate is
removed last, while the metal layer near the perimeter or
edge of the substrate is cleared first. For example, Fig.
20   13A shows that the metal layer within a radius range of 0-
20mm is removed at about 330 seconds. Fig. 13B shows that
the metal layer within a radius range of 20-30 mm is removed
at about 325 seconds. Fig. 13C shows that the metal layer
within a radius range of 30-40mm is removed at about 318
25   seconds. Fig. 13D shows that the metal layer within a
radius range of 40-50mm is removed at about 310 seconds.
Fig. 13E shows that the metal layer within a radius range of
50-60mm is removed at about 295 seconds. Fig. 13F shows
that the metal layer within a radius range of 60-70mm is
30   removed at about 290 seconds. Fig. 13G shows that the metal
layer within a radius range of 70-80mm is removed at about
290 seconds; and Fig. 13H shows that the metal layer within
a radius range of 80-90mm is removed as early as about 260
seconds.

35   As shown therein, the reflectance trace for several
of the radial ranges exhibit two intensity levels (shown by

24

lines 160 and 162). The distance between the two intensity levels increases with substrate radius. Without being limited to any particular theory, the two intensity levels may be caused by non-symmetric distribution of the slurry or the product of the reaction of the slurry and the metal layer on the substrate. Specifically, on each sweep of the laser beam across the substrate, two data points are usually entered in a bin: one data point which is closer to the leading edge of the substrate and one data point which is closer to the trailing edge of the substrate. However, due to non-symmetric distribution of the slurry and the reaction products beneath the substrate, the laser beam may be more attenuated when passing through slurry layer adjacent different regions of the substrate. Thus, the reflectance traces might also be used as a measure of the uniformity of slurry distribution beneath the substrate.

In another implementation, an operator might decide to use only a single bin. In this case, all of the intensity measurements for the specified radial range are used to determine a single intensity trace, which is used for determination of a polishing endpoint in the conventional fashion. The operator can specify this radial range based on examination of the transient signal graphs. For example, if the transient signal graphs show that the center of the substrate is the last portion to be polished, then the operator can select a radial range around the substrate center to ensure that the endpoint is not triggered until all of the metal has been polished away.

The reflection intensity changes during polishing are thus captured for different radial positions on the substrate. The high resolution data acquisition allows a precise time control of each process step in a multi-step operation. A wealth of parameters such as uniformity of the entire wafer and removal rate for different radial portions of the wafer are captured. The acquired high resolution data can be processed on-line or off-line to adjust various

variables and parameters to minimize erosion and dishing of
the surface layer. If the data is processed in real-time,
the real-time feedback data allows a tighter closed-loop
control with the process parameters. Further, the
5   reflection data is available for process engineers to
experiment with their processing parameters to improve the
polishing process.

The present invention has been described in terms of
a preferred embodiment. The invention, however, is not
10   limited to the embodiment depicted and described. Rather,
the scope of the invention is defined by the appended
claims.

WHAT IS CLAIMED IS:

1.   A method for determining an endpoint associated with
chemical mechanical polishing a metal layer on a substrate,
5   the endpoint having a predetermined pattern reflected of
reflected high intensity, the method comprising:
        bringing a surface of the substrate into contact
with a polishing pad that has a window;
        causing relative motion between the substrate and
10 the polishing pad;
        directing a light beam through the window, the
motion of the polishing pad relative to the substrate
causing the light beam to move in a path across the
substrate;
15   detecting light beam reflections from the metal
layer;
        generating reflection data associated with the light
beam reflections;
        dividing the reflection data into a plurality of
20 radial ranges; and
        identifying the predetermined pattern from the
reflection data in the plurality of radial ranges to
establish the endpoint.

25 2.   The method of claim 1, further comprising stopping
chemical mechanical polishing when the endpoint is
identified.

3.   The method of claim 1, further comprising storing
30 the reflection data on a media for subsequent analysis.

4.   The method of claim 3, further comprising processing
the reflection data in real-time.

35 5.   The method of claim 3, further comprising processing
the reflection data off-line.

6.   The method of claim 1, wherein the identifying step
further comprises comparing the reflection data to a
predetermined threshold.

5   7.   The method of claim 1, wherein the identifying step
further comprises determining whether the reflection data is
in a downward trend.

8.   The method of claim 1, wherein the identifying step
10   further comprises determining whether the reflection data is
in an upward trend.

9.   The method of claim 1, wherein the identifying step
further comprises determining whether the reflection data is
15   in a flat trend.

10.   The method of claim 1, wherein the detecting step
measures reflections corresponding to a sampling zone in the
path across the substrate, the method including:
20   determining a radial position for each sampling
zone;
            determining a position of the carrier head from a
carrier head sweep profile; and
            dividing the reflection measurements into a
25   plurality of radial ranges according to the radial position.

11.   A method for determining an endpoint associated with
chemical mechanical polishing a metal layer, the endpoint
having a predetermined pattern of reflected light intensity,
30   the method comprising:
            directing a light beam through a window of a
polishing pad and moving the polishing pad relative to the
substrate to cause the light beam to move in a path across
the substrate;
35   detecting light beam reflections from the metal
layer;

28

generating reflection data associated with the light
beam reflections;

dividing the reflection data into a plurality of
radial ranges; and

5   identifying the predetermined pattern from the
reflection data in the plurality of radial ranges to
establish the endpoint.

12.   The method of claim 11, further comprising stopping
10   chemical mechanical polishing when the endpoint is
identified.

13.   The method of claim 11, further comprising storing
the reflection data on a media for subsequent analysis.
15

14.   The method of claim 11, wherein the identifying step
comprises comparing the reflection data to a predetermined
threshold.

20   15.   The method of claim 11, wherein the identifying step
further comprises determining whether the reflection data
has a downward trend, an upward trend or a flat trend.

16.   An apparatus for polishing a metal layer of a
25   substrate, comprising:

a carrier head to hold the substrate;

a polishing pad adapted to contact a surface of the
substrate, the polishing pad having a window therethrough;

a motor coupled to the polishing pad for causing
30   relative motion between the substrate and the polishing pad;

a light source to direct a light beam through the
window, the motion of the polishing pad relative to the
substrate causing the light beam to move in a path across
the substrate;

35   a sensor optically coupled to the light source for
detecting light beam reflections from the substrate, the

sensor generating reflection data associated with the light beam reflections;

an electronic bin coupled to the sensor for separating the reflection data into a plurality of radial ranges; and

a pattern recognizer coupled to the sensor and to the bin for identifying the endpoint by comparing the predetermined pattern to the reflection data.

17.   The apparatus of claim 16, further comprising a polishing controller coupled to the pattern recognizer, the polishing controller stopping chemical mechanical polishing when the endpoint is identified.

18.   The apparatus of claim 16, wherein the reflection data is stored on a media for subsequent analysis.

19.   The apparatus of claim 16, wherein the pattern recognizer compares the reflection data to a predetermined threshold.

20.   The apparatus of claim 16, wherein the pattern recognizer determines whether the reflection data has a downward trend, an upward trend or a flat trend. 1. A method of determining polishing parameters, comprising:

bringing a surface of a substrate into contact with a polishing pad that has a window;

causing relative motion between the substrate and the polishing pad;

directing a light beam through the window, the motion of the polishing pad relative to the substrate causing the light beam to move in a path across the substrate;

detecting light beam reflections from a layer in the substrate;

generating reflection data associated with the light

beam reflections;

      displaying the reflection data from a scan of the
light beam across the substrate; and

      selecting polishing parameters to provide uniform
5 polishing of the substrate based on the displayed reflection
data.

21.   A method of determining polishing parameters,
comprising:

10   bringing a surface of a substrate into contact with
a polishing pad that has a window;

      causing relative motion between the substrate and
the polishing pad;

      directing a light beam through the window, the
15 motion of the polishing pad relative to the substrate
causing the light beam to move in a path across the
substrate;

      detecting light beam reflections from a layer in the
substrate; .

20   generating reflection data associated with the light
beam reflections;

      displaying the reflection data from a scan of the
light beam across the substrate; and

      selecting polishing parameters to provide uniform
25 polishing of the substrate based on the displayed reflection
data.

22.   A method of determining process uniformity,
comprising:

30   detecting light beam reflections during polishing of
a layer in a first substrate;

      detecting light beam reflections during polishing of
a layer in a second substrate;

      generating reflection data associated with the light
35 beam reflections;

      displaying reflection data from a first scan of the

31

light beam across the first substrate;

displaying reflection data from a second scan of the
light beam across the second substrate; and

comparing the reflection data from the first scan to
5   the reflection data from the second scan to determine
process uniformity.

23.   The method of claim 22, further comprising changing
a polishing consumable between the polishing of the first
10   and second substrates.

FIG._1

FIG._2

FIG._3

FIG._4

FIG._8

FIG._5A

FIG._5B

FIG._5C

FIG._5D

FIG._5E

FIG._6

```
                          ┌─────────────────┐ 101
                          │ STORE POLISHING │        100
                          │   PARAMETERS    │
                          └────────┬────────┘
                                   │         102
                          ┌────────▼────────┐
                          │     PERFORM     │
                          │    POLISHING    │
                          └────────┬────────┘
                                   │         104
                          ┌────────▼────────┐
                          │  COLLECT SIGNAL │
                          └────────┬────────┘
                                   │
              ┌────────────────────┴────────────────────┐
              │ 106                                      │ 114
     ┌────────▼────────┐                      ┌──────────▼──────────┐
     │    DISPLAY      │                      │ STORE TRANSIENT DATA│
     │   TRANSIENTS    │                      └──────────┬──────────┘
     └────────┬────────┘                                 │ 116
              │ 108                            ┌──────────▼──────────┐
     ┌────────▼────────┐                      │DETERMINE INTENSITY  │
     │  APPLY SIGNAL   │                      │  FOR EACH SAMPLING  │
     │  RECOGNITION    │                      │        ZONE         │
     │   ALGORITHM     │                      └──────────┬──────────┘
     │                 │                                 │ 118
     │ DETECT SIGNAL   │                      ┌──────────▼──────────┐
     │    CHANGES      │                      │ CALCULATE RADIAL    │
     └────────┬────────┘                      │   POSITION OF       │
              │ 110                            │ EACH SAMPLING ZONE  │
     ┌────────▼────────┐                      └──────────┬──────────┘
     │ SEND FEEDBACK   │                                 │ 150
     │  TO POLISHER    │                      ┌──────────▼──────────┐
     │  CONTROLLER     │                      │ SORT INTENSITY      │
     └────────┬────────┘                      │  MEASUREMENTS       │
              │ 112                            │ INTO RADIAL RANGES  │
     ┌────────▼────────┐                      └──────────┬──────────┘
     │  STOP POLISHING │                                 │ 152
     └─────────────────┘                      ┌──────────▼──────────┐
                                              │ USE SORTED DATA TO  │
                                              │ MEASURE POLISHING   │
                                              │UNIFORMITY AND REMOVAL│
                                              │RATES AT DIFFERENT   │
                                              │   RADIAL RANGES     │
                                              └─────────────────────┘
```

```
   130
   ┌──────────────────────┐    132   ┌──────────────────────┐ 134
   │ DETERMINE TIME T_SYM │          │  DETERMINE RADIAL    │
   │  WHEN LASER BEAM     │─────────▶│   POSITION FROM      │
   │ PASSES BENEATH       │          │ DIFFERENCE BETWEEN   │      FIG._9A
   │MIDLINE OF SUBSTATE   │          │  MEASUREMENT TIME    │
   └──────────────────────┘          │  T_MEASURE AND       │
                                     │ SYMMETRIC TIME T_SYM │
                                     └──────────────────────┘
```

FIG._7A

FIG._7B

FIG._9B

FIG._10

8 / 11

FIG._11

FIG._13A

FIG._13B

FIG.__12

Legend:

1.7-2.7 s		300
19.9-20.9 s		302
66.0-67.0 s		304
159.5-160.5 s		306
229.3-230.3 s		308
268.4-269.4 s		310
283.8-284.8 s		312
306.1-307.1 s		316
325.6-326.6 s		318
350.8-351.8 s		320

NO TOPOGRAPHY LEFT

2

EFFECT OF PATTERN

STARTING TO CLEAR CU

ALL CLEARED EXCEPT CENTER

NORMALIZED TIME [s]

SIGNAL

FIG._13C

FIG._13D

FIG._13E

11 / 11

FIG._13F

FIG._13G

FIG._13H

INTERNATIONAL SEARCH REPORT

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7   G01B11/06   B24B37/00   H01L21/304

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7   G01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 663 265 A (IBM) 19 July 1995 (1995-07-19) column 10, line 16 - line 24 column 12, line 24 - line 57; figures 3-5,7 —	1,11,16
A	US 5 427 878 A (DEC) 27 June 1995 (1995-06-27) column 5, line 14 - line 40; figures 1,4,5 —	1,11,16
A	JP 09 085611 A (EBARA) 31 March 1997 (1997-03-31) figures 1,2,4A,4B —	1,11,16
	-/-	

[X] Further documents are listed in the continuation of box C.   [X] Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
17 February 2000	06/03/2000

Name and mailing address of the ISA	Authorized officer
European Patent Office, P.B. 5818 Patentlaan 2 NL – 2280 HV Rijswijk Tel. (+31–70) 340–2040, Tx. 31 651 epo nl, Fax: (+31–70) 340–3016	Mielke, W

Int   ional Application No

PCT/US 99/25639

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication,where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 738 561 A (APPLIED MATERIALS) 23 October 1996 (1996-10-23) column 2, line 45 - line 51 column 21, line 49 -column 22, line 48; figure 16	21
A	US 5 663 797 A (MICRON) 2 September 1997 (1997-09-02) column 2, line 63 - line 66	22

INTERNATIONAL SEARCH REPORT

Information on patent family members

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
EP 0663265	A	19-07-1995	US	5433651 A	18-07-1995
			DE	69410772 D	09-07-1998
			DE	69410772 T	25-02-1999
			JP	2561812 B	11-12-1996
			JP	7235520 A	05-09-1995
US 5427878	A	27-06-1995	DE	4221074 A	07-01-1993
			FR	2678426 A	31-12-1992
			GB	2257507 A,B	13-01-1993
			JP	6151297 A	31-05-1994
JP 9085611	A	31-03-1997	US	5838447 A	17-11-1998
EP 0738561	A	23-10-1996	US	5964643 A	12-10-1999
			JP	9007985 A	10-01-1999
			US	5893796 A	13-04-1999
US 5663797	A	02-09-1997	US	5910846 A	08-06-1999